






















Product quality	
Formats	730 x 146 x 5,0 mm
Packaging	Pack: 18 elements / 1,918 m ² / 19,364 kg
	Pallet: 48 packs / 92,085 m ² / 929,461 kg

Tolerances (Requirement EN ISO 10582)		
Weight per unit area	10.100 g/m ² +13%/-10%	
Squareness of the elements (≤ 0.25mm)	≤ 0,20 mm	
Determination of Linearity (≤ 0.35 mm/m)	≤ 0,30 mm/m	
Dimensional stability after exposure to heat (≤ 0,15 %)	≤ 0,15%	
Curling after exposure to heat (≤ 1mm)	≤ 1 mm/m	
Flatness concave / convex	lengthwise (≤ 0.50/≤ 1.0 %)	≤ 0,50/≤ 1,00 %
	wide (≤ 0.15/≤ 0.20 %)	≤ 0,15/≤ 0,20 %
Surface flushness	(average ≤ 0.10 mm)	(average ≤ 0.10 mm)
	(max. ≤ 0.15 mm)	(max. ≤ 0.15 mm)
Opening between installed elements	(average ≤ 0.15 mm)	(average ≤ 0,15 mm)
	(max. ≤ 0.20 mm)	(max. ≤ 0.10 mm)

Guarantee (according Parador guarantee conditions)		Notes
Domestic area	Commercial area	- suitable for all-over adhesion (see notes in our advisor)
Lifetime	10 years	- cleaning an maintenance see instructions
		- technical changes reserved

Classification		
		
Utility class 23 = domestic areas with intensive use	Utility class 33 = commercial areas with intensive use	
The design floor meets all requirements of the designated utility class.		
Requirements / properties	Test method	Rating
 Wear layer	ISO 24340	0,55 mm
 Surface Coating		PUR
 Reaction to fire	EN 13501-1	B _n -s1
 Slip resistance	EN 13893 EN 14041	μ ≥ 0,30 DS
 Staining resistance	EN 438-2	Category 1 + 2: level 5, no visible change Category 3: level 4, slight change
 Light fastness	EN ISO 105 - B02	Blue wool scale: Stage ≥ 6
 Resistance to roller castor chairs	EN ISO 4918	Type W, no visible changes
 Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay	EN 12667	0,030 m ² *K/W
 Moving a furniture leg	EN ISO 16581	No visible damage (foot type 0)
 Indentation-residual	EN ISO 24343-1	≤ 0,10 mm
 Abrasion	ISO 24338, Procedure B	> 5.000 rev.
 Dimensional stability	EN ISO 23999	≤ 0,20 %
 Water resistance	EN 317	waterproof
 Micro scratch resistance	EN 16094	Method A MSR-A1 For mat surfaces (gloss ≤ 7): ≤ 1,5 unit change at 60°
 Antimicrobial activity	ISO 22196	Antibacterial
 Disposal	EAK-Code-number	20 01 39

Changed:	QMB Parador	File:	PA_TDS_Designboden_Vinyl_Trendtime-3_EN_20240101
Date:	01.11.2023	Latest update at:	https://parador.de/en/services/downloads/design-flooring
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.01.2024